Prowax[™] 390 Page 1 of 2

ExonMobil

Prowax™ 390

ExxonMobil Specialties, Ecuador

Product Description

Prowax 390 is a high-range melting point product in the Prowax line of petroleum slack and scale waxes. It is a translucent crystalline material in the solid state yellow, clear liquid when molten. It is derived from petroleum via a carefully controlled refining process and is primarily comprised of a mixture of straight chain r paraffin and branched, iso-paraffin hydrocarbons.

ExxonMobil waxes are produced and controlled according to the ExxonMobil Product Quality Management System, EN ISO 9000 or equivalent standard

Applications

Prowax 390 can be used in the following applications subject to applicable laws and regulations in each jurisdiction*:

- Firelogs
- Wax emulsions
- Wax blends

Properties and Specifications

Property	Standard Method(a)	Min	Max
ASTM Color by Auto Tristimulus	ASTM D6045		6.0
Congealing Point, °C	ASTM D938	68.0(154.4)	81.0(177.8)
Flash Point, Cleveland Open Cup, °C (F)	ASTM D92	232(450)	
Kinematic Viscosity @ 100 C, mm2/s	ASTM D445	16.0	20.5
Oil Content, wt%	ASTM D721		5.0

Note 1: Products are certified on release to meet the values specified. Actual values may deviate within the established reproducibility of the test method specified.

Note 2: For purpose of determining conformance with specification, observed or calculated values shall be rounded off to the nearest unit in the last significant dig in expressing the limiting value in accordance to the ASTM E 29 method

(a) In lieu of standard test method, alternate test methods may be used for the certification of a product property.

Health and safety

 $Health \ and \ Safety \ recommendations \ for \ this \ product \ can \ be \ found \ on \ the \ Material \ Safety \ Data \ Sheet \ (MSDS) \ @ \ http://www.msds.exxonmobil.com/psims/psims.as$

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

10-2023

TERPEL-LUBRICANTES ECUADOR S.A.S.

Av. Joaquin Orrantia 125 y Av. de las Américas, Edificio Solaris, Piso 12, Oficinas 801-812, Guayaquil, Ecuador

Teléfono: (593) 4-3811980

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

^{*} User must check compliance with applicable regulations

Prowax™ 390 Page 2 of 2

