



ASPHALT EMULSION EAP

ExxonMobil Asphalt , Cambodia
Emulsified Asphalt Prime Asphalt Emulsion

Product Description

Asphalt Emulsion EAP is an emulsified asphalt prime asphalt emulsion produced by the patented SMEP process. The base asphalt for emulsification is derived from specially selected crude oils via carefully controlled refining processes. Asphalt Emulsion EAP components are carefully selected and balanced, according to formula developed by ExxonMobil.

The quality of ExxonMobil products is assured for every delivery. They are produced and controlled according to the ExxonMobil Product Quality Management System EN ISO 9000 or equivalent standard.

Applications

Asphalt Emulsion EAP is recommended for road construction. If other applications are considered, then users should conduct appropriate testing before use.

Claims

| |
|--|
| This product meets or exceeds the requirements of: |
| Specification no. DH-SP 410/2014 of Department of Highways, Thailand |

Properties and Specifications

| Property | Standard Method(a) | | Limit |
|--|--------------------|---------|----------|
| Ductility @ 25 C, 5 cm/min, on Distillation Residue, cm | ASTM D113 | Min | 40 |
| Solubility in Trichloroethylene, Distillation Residue, wt% | ASTM D2042 | Min | 97.5 |
| Penetration, 25 C, on Distillation Residue, 0.1 mm | ASTM D5 | Min-Max | 100-250 |
| Settlement, 5 days, Difference, % | ASTM D6930 | Max | 10 |
| Storage Stability, 24 h, Difference, % | ASTM D6930 | Max | 2 |
| Sieve Test, Retained on No. 20, wt% | ASTM D6933 | Max | 0.1 |
| Distillation Residue, wt% | ASTM D6997 | Min | 50 |
| Particle Charge | ASTM D7402 | Min-Max | Positive |
| Saybolt-Furol Viscosity @ 25 C, s | ASTM D7496 | Min-Max | 20-100 |
| Penetration Power Test, timing of permeability into standard filler, minutes | EN 12849 (mod) | Max | 20 |
| Penetration Power Test, distance of permeability into standard filler, mm. | EN 12849 (mod) | Min | 8 |
| Oil Distillate, by Volume of Emulsion, % | ASTM D6997 | Min-Max | 5-12 |


Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

08-2020

ExxonMobil



© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved