Paving Asphalt 60/70 S Page 1 of 2

ExonMobil

Paving Asphalt 60/70 S

ExxonMobil Asphalt, Singapore

PENETRATION GRADED ASPHALT PRODUCT

Product Description

Paving Asphalt 60/70 S is a penetration graded asphalt product derived from specially selected crude oils via carefully controlled refining processes.

The quality of ExxonMobil products is assured for every delivery. They are produced and controlled according to the ExxonMobil Product Quality Management S EN ISO 9000 or equivalent standard.

Applications

Paving Asphalt 60/70 S is recommended for road construction. If other applications are considered, then users should conduct appropriate testing before use.

Properties & Specifications

Paving Asphalt 60/70 S meets the following specification requirements:

Asphalt	Unit	Method	60/70 S
Penetration at 25° C	x 0.1 mm	ASTM D 5	60-70
Softening Point	°C	ASTM D 36	47-56
Ductility at 25° C, 5 cm/min (min)	cm	ASTM D 113	150
Wax content (max)	mass %	DIN EN 12606-1	2
Specific gravity	-	ASTM D 70	1.01-1.05
Flash Point (min)	°C	ASTM D 92	232
Solubility in trichloroethylene (min)	mass %	ASTM D 2042	99.5

Thin Film Oven Test at 163° C (ASTM D1754)

Change of mass (max) +/-	mass %	ASTM D 1754	0.2
Retained penetration (min)	%	ASTM D 5	60
Ductility at 25° C , 5 cm/min (min)	cm	ASTM D 113	100

Above specifications may be subject to change.

Health & Safety

Detailed health and safety information for this product is provided in the Material Safety Data Sheet (MSDS), available upon request through your loca representative or from www.ExxonMobil.com

All trademarks used herein are trademarks of Exxon Mobil Corporation or one of its subsidiaries.

02-2021

Further Information

ExxonMobil supplies a full range of bitumen, waxes, white oils, process oils and a full range of other lubricants, fuels and chemical products worldwide. Please c

Paving Asphalt 60/70 S Page 2 of 2

your local ExxonMobil representative, or contact us at www.exxonmobil.com for more information on other products.

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

