Prowax 401 Page 1 of 2

ExonMobil

Prowax 401

ExxonMobil Specialties, Senegal

Product Description

Prowax 401 is a low-range melting point product in the Prowax line of petroleum slack and scale waxes. It is a translucent crystalline material in the solid state tan-to-light amber colored, clear liquid when molten. It is derived from petroleum via a carefully controlled refining process. Prowax 401 is comprised of a mixi straight chain normal paraffin and branched, iso-paraffin hydrocarbons.

These products are produced and controlled according to the ExxonMobil Product Quality Management System, EN ISO 9000 or equivalent standard.

Applications

Prowax 401 can be used in the following applications subject to applicable laws and regulations in each jurisdiction*:

- Candles
- Wax emulsions

Properties and Specifications

Property	Standard Method(a)	Min	Max
ASTM Color by Auto Tristimulus	ASTM D6045		1.0
Flash Point, Cleveland Open Cup, °C	ASTM D92	180	
Kinematic Viscosity @ 100 C, mm2/s	ASTM D445	2.6	3.4
Melting Point, °C	ASTM D87	44.0	51.0
Oil Content, wt%	ASTM D721		10.0

Note 1: Products are certified on release to meet the values specified. Actual values may deviate within the established reproducibility of the test method specified.

Note 2: For purpose of determining conformance with specification, observed or calculated values shall be rounded off to the nearest unit in the last significant dig in expressing the limiting value in accordance to the ASTM E 29 method

(a) In lieu of standard test method, alternate test methods may be used for the certification of a product property.

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

02-2024

Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

^{*} User must check compliance with applicable regulations

Prowax 401 Page 2 of 2

