



Mobil SHC™ Grease 681 WT

Mobil Grease , Brazil

High Performance Synthetic Grease for Wind Turbines

Product Description

Mobil SHC™ Grease 681 WT is specially formulated to lubricate yaw, pitch and main bearings of wind turbines. It is a high performance synthetic lithium complex specially designed to exceed the demanding requirements of wind turbine applications at extreme temperatures. The advanced synthetic base fluid with its low tr coefficient provides excellent low temperature pumpability and very low starting and running torque.

Features and Benefits

- Superb thermal stability and oxidation resistance compared to conventional greases helps provide extended service life with longer relubrication intervals fo turbines
- Outstanding low temperature performance compared to conventional greases provides excellent protection at low temperatures providing low torque an start-up at low temperatures
- Excellent rust and corrosion protection provides enhance performance in wet conditions for reduced downtime and maintenance costs compared to/ conventional greases
- Outstanding structural stability in the presence of water helps retain grease consistency in hostile aqueous environments
- Excellent low temperature pumpability provides reliable lubrication of bearings using centralized grease systems or grease dispensers.
- Low traction base oil coefficient offers potential improved mechanical life and reduced energy costs versus conventional greases.
- Increased oil viscosity for extra protection with excellent low temperature properties
- No dye for improved housekeeping
- Excellent performance in the Wind Industry Riffel test

Applications

- Mobil SHC Grease 681 WT is an NLGI 1.5 Grade extreme pressure grease with ISO VG 680 synthetic base fluid recommended for tough wind turbine applic requiring addition EHL protection
- Mobil SHC Grease 681 WT meets most specifications of wind turbine builders and component suppliers and can demonstrated outstanding performance lubrication of yaw, pitch, and generator bearings either manual greased or using centralized grease systems or grease dispensers.
- Recommended application temperature range for continuous operation is from -40° C to 150°C with proper regreasing intervals

Typical Properties

	Mobil SHC Grease 681 WT
NLGI Grade	1.5
Thickener Type	Lithium Complex
Colour, Visual	Beige
Penetration, Worked, 25°C, ASTM D 217	305
Dropping Point, °C, ASTM D 2265	260
Viscosity of Oil, ASTM D 445,cSt 40°C	680
Viscosity of Oil, ASTM D 445,cSt100°C	74
Roll Stability, Pen Change, ASTM D 1831, mm/10	10
4-Ball Wear Scar, ASTM D 2266	0.6
4-Ball Weld, ASTM D 2596, Load, Kg	250
Water Washout, ASTM D 1264, Loss at 79°C. % wt	7
EMCOR Rust Test, 10 % Synthetic Sea Water, ASTM 6138	0,0

	Mobil SHC Grease 681 WT
Corrosion Protection, ASTM D 1743, Rating	Pass
Copper Strip Corrosion, ASTM D 4048, Rating	1a

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

06-2023
Cosan Lubrificantes e Especialidades S.A.
Praia da Ribeira, 01
21930-080 Rio de Janeiro – RJ - BRASIL
Tel: 0800 644 1562

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entity.

ExxonMobil

Exxon

Mobil

Esso

XTOMobil

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved