

**Mobil Centaur XHP™ 221**

Mobil Grease , United Kingdom

Multipurpose Calcium Sulphonate Complex Grease

**Product Description**

Mobil Centaur XHP 221 premium multipurpose grease has been formulated to lubricate rolling element bearings in industrial machinery operating at high temperatures under wet, heavily loaded conditions.

**Features and Benefits**

Mobil Centaur XHP 221 offers the following features and benefits :

Features	Advantages and Potential Benefits
Excellent resistance to water and corrosion	The calcium sulphonate thickener system protects against water washout and bearing corrosion under challenging conditions
Exceptional mechanical stability	Resists softening under mechanical shear in the presence of process water contamination.
High load carrying properties	Excellent extreme pressure protection at low to moderate speeds is provided by the grease thickener system.
Excellent thermal stability	Resists oxidation and oil separation at high temperatures, and provides excellent life in accelerated bearing life tests.

**Applications**

Mobil Centaur XHP 221 is recommended for lubrication of rolling element bearings in machinery operating at high temperatures where resistance to water washout and corrosion are important. Specific examples of such applications include :

- Wet-end paper machine bearings
- Heavily loaded industrial ball and roller bearings
- Bearings in steel mill and mining operations

**Specifications and Approvals**

<b>This product meets or exceeds the requirements of:</b>
DIN 51825: 2004-06 KPF1-2G-20

**Properties and Specifications**

Property	
Grade	NLGI 1.5
Thickener Type	Calcium Sulfonate
SKF Emcor Rust Test, Acidic Water, ASTM D6138	1 , 1
Water Washout, Loss @ 79 C, wt%, ASTM D1264	1

Property	
Color, Visual	Brown
Oil Separation, 30 h @ 100 C, mass%, ASTM D6184	0.5
Four-Ball Wear Test, Scar Diameter, mm, ASTM D2266	0.45
Oil Separation, 168 h @ 40 C, mass%, DIN 51817	0.3
Four-Ball Extreme Pressure Test, Weld Point, kgf, ASTM D2596	500
Viscosity Index, ASTM D2270	94
Viscosity @ 100 C, Base Oil, mm2/s, ASTM D445	18.7
Viscosity @ 40 C, Base Oil, mm2/s, ASTM D445	220
Dropping Point, °C, ASTM D2265	>308
Timken OK Load, kg, ASTM D2509	55
SKF Emcor Rust Test, Distilled Water, ASTM D6138	1 , 1
Copper Strip Corrosion, 24 h, 100 C, Rating, ASTM D4048	1A
Penetration, 60X, 0.1 mm, ASTM D217	305
Corrosion Preventive Properties, Rating, ASTM D1743	Pass

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

03-2024  
Esso Petroleum Company limited  
ExxonMobil House, Ermyn Way, Leatherhead, Surrey KT22 8UX

You can always contact our Technical Help Desk engineers on Mobil lubricants and services related questions: <https://www.mobil.co.uk/en-gb/contact-us-technica>  
44 (0)1372 222000  
<http://www.exxonmobil.com>

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product perfor are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All pr may not be available locally. For more information, contact your local ExxonMobil contact or visit [www.exxonmobil.com](http://www.exxonmobil.com)

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is inten override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

ExxonMobil

Exxon

Mobil

Esso

XTO

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved