



Mobilgear MS Series

Mobil Industrial , Hong Kong

Gear Oils

Product Description

Mobilgear™ MS Series are extra high performance oils designed for the oil-fog or mist-lubrication of machine components such as slideways, bearings, gears, chains. They are formulated from high quality, solvent refined base stocks and a unique additive system designed for optimum reclassifying properties. They have resistance to oxidation and good extreme pressure and anti-wear properties. The products have enhanced surface wetting capabilities and they reclassify agglomerate readily from a mist to a liquid when the mist is subjected to extreme turbulence or is impinged onto a surface at high velocity. This allows a lubricating film to form on bearings and gears and prevents stray mist from escaping through narrow apertures into the atmosphere.

The four viscosity grades in the Mobilgear MS Series, ranging from ISO VG 32 to 460, allow the machine designer to choose the product most suitable for proper lubrication of machine elements. The heavier grades are used on ways, gears, and slow-speed, heavily loaded bearings, while the lower viscosity grades are used on high-speed bearings.

Features and Benefits

The Mobilgear MS Series of products is an important member of the Mobil brand of lubricants and enjoy recognition among equipment operators for their superior performance capabilities in misting applications. Mobilgear MS Series oils were developed specifically for mist applications and have undergone an arduous performance testing, including misting performance, in their development.

Mobilgear MS Series offer the following features and potential benefits:

| Features   | Advantages and Potential Benefits   |
|--|---|
| Superior mist forming and reclassifying properties | Ensures even distribution of lubricant on machine parts with control of stray mist for reliable lubrication and problem-free operation, reduced leakage and lower oil consumption |
| Excellent EP and anti-wear performance             | Prevents machine element wear with resulting savings in maintenance and parts replacement   |
| High quality base oil and additive components      | Avoids reclassifier plugging problems which can result in catastrophic bearing and gear failure, with accompanying downtime and replacement costs                                 |
| Excellent resistance to oxidation                  | Long product life, reduced product and maintenance costs  |
| Very good rust protection including sea water      | Excellent equipment protection  |

Applications

Mobilgear MS Series oils are designed for use in all oil mist lubrication systems. Such systems work by dispersing very small droplets of oil in a smoothly flowing air stream, distributing the oil mist to the points of application and mechanically condensing the mist, causing the oil to impinge on and wet the surfaces to be lubricated. The viscosity of Mobilgear MS grades may require thermal misting devices to form proper dispersions when ambient temperatures are moderate or low. Mobilgear MS is suitable for oil / air delivery systems such as airline oilers. Specific applications include:

- Industrial gearing such as cooling tower gearboxes
- Slow-speed, heavily-loaded bearings (higher viscosity grades)
- High-speed bearings (lower viscosity grades)
- Machine tools, ways and screws
- Process pumps, electric motors and blowers
- Steam turbines and electric motors

Properties and Specifications

| Property   | 32     | 100     | 320     | 460     |
|--|--------|---------|---------|---------|
| Grade  | ISO 32 | ISO 100 | ISO 320 | ISO 460 |
| Density @ 15.6 C, kg/l, ASTM D4052   | 0.88   | 0.89    | 0.90    | 0.90    |
| EP Properties, Timken OK Load, lb, ASTM D2782                                  |        | 65      | 65      | 65      |
| FZG Scuffing, Fail Load Stage, A/8.3/90, ISO 14635-1                           | 12+    | 12+     | 12+     | 12+     |
| Flash Point, Cleveland Open Cup, °C, ASTM D92                                  | 210    | 234     | 230     | 238     |
| Four-Ball Extreme Pressure Test, Load Wear Index, kgf, ASTM D2783              |        | 48      | 48      | 48      |
| Four-Ball Extreme Pressure Test, Weld Load, kgf, ASTM D2783                    |        | 250     | 250     | 250     |
| Four-Ball Wear Test, Scar Diameter, 20 kg, 1800 rpm, 1 h, 54 C, mm, ASTM D4172 |        | 0.3     | 0.3     | 0.3     |
| Kinematic Viscosity @ 100 C, mm2/s, ASTM D445                                  | 5.5    | 11.2    | 25      | 31.5    |
| Kinematic Viscosity @ 40 C, mm2/s, ASTM D445                                   | 32     | 100     | 320     | 460     |
| Pour Point, °C, ASTM D97   | -12    | -12     | -9      | -6      |
| Rust Characteristics, Procedure B, ASTM D665                                   | PASS   | PASS    | PASS    | PASS    |
| Viscosity Index, ASTM D2270  | 110    | 95      | 100     | 100     |

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

12-2019  
ExxonMobil Hong Kong  
22nd Floor, Central Plaza,  
18 Harbour Road, Wanchai  
Hong Kong  
+852 3197 8888  
<http://www.exxonmobil.com>

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit [www.exxonmobil.com](http://www.exxonmobil.com)  
ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entity.

ExxonMobil

Exxon

Mobil

Esso

XT

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved