



Mobil SHC™ Grease 102 WT

Mobil Industrial , Japan

High Performance Synthetic Grease for Wind Turbines

Product Description

Mobil SHC™ Grease 102 WT is scientifically engineered to meet or exceed the demanding requirements for severe wind turbine pitch and yaw applications at extreme cold temperatures. The unique features of synthetic base fluids are combined with those of a high quality lithium complex thickener. This state-of-the-art formulation helps contribute to excellent extreme low temperature application as well as high-temperature performance with powerful structural stability and resistance to water washout.

Features and Benefits

- The low internal friction and high natural viscosity index of the base fluids offers the potential for improved low-temperature starting and running torque pumpability down to -50 °C (-58° F).
- Superb thermal stability and oxidation resistance compared to conventional greases helps provide extended service life with longer relubrication intervals.
- Excellent rust and corrosion protection provides excellent performance in wet conditions for reduced downtime and maintenance costs compared to conventional greases.
- Outstanding structural stability in the presence of water helps retain grease consistency in hostile aqueous environments.
- Excellent pumpability provides reliable lubrication of bearings using centralized grease systems or grease dispensers.
- Low traction coefficient offers potential improved mechanical life and reduced energy costs versus conventional greases.

Applications

- Mobil SHC Grease 102 WT meets most specifications of wind turbine builders and component suppliers and has demonstrated outstanding performance lubrication of yaw, pitch, and generator bearings either manually greased or using centralized grease systems or grease dispensers.
- For wind turbines operating under extreme low temperature environments.
- Recommended application temperature range for continuous operation is from -50° C (-58° F) to 120°C (248° F).

Specifications and Approvals

<b>This product has the following approvals:</b>
Tested and approved for material compatibility by IMO
Tested and approved for seal compatibility by ThyssenKrupp Rothe Erde

<b>This product meets or exceeds the requirements of:</b>
DIN 51825: 2004-06 KPHC2K-50

Properties and Specifications

Property	
Grade	NLGI 2
Corrosion, Bearing, 48 h, 52 C, Rating, ASTM D1743	PASS
Dropping Point, °C, ASTM D2265	263

Property	
Four-Ball Extreme Pressure Test, Weld Load, kgf, ASTM D2596	315
Penetration, 60X, 0.1 mm, ASTM D217	285
SKF Emlcor Rust Test, Distilled Water, ASTM D6138	0, 0
Water Washout, Loss @ 79 C, wt%, ASTM D1264	6

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>  
All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

09-2020  
ExxonMobil Japan Godo Kaisha  
Shinagawa Grand Central Tower  
2-16-4, Konan, Minato-Ku,  
Tokyo, 108-8218,  
Japan

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All properties may not be available locally. For more information, contact your local ExxonMobil contact or visit [www.exxonmobil.com](http://www.exxonmobil.com)  
ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entity.

ExxonMobil

Exxon

Mobil

Esso

XTL

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved