Mobil Arapen™ RB 320 Page 1 of 2



Mobil Arapen™ RB 320

Mobil Grease, Panama

Grease

Product Description

Mobil Arapen RB 320 is a high performance long-life grease developed for the roller bearings of railroad car journals where no provision is provided for inequilibrication. It is formulated with a mineral base fluid and a mixed lithium / calcium soap thickener. Mobil Arapen RB 320 grease has the high oxidation stability reto maintain good lubrication throughout extended periods of service or storage. It is highly resistant to chemical deterioration that might otherwise produce as deposits that are detrimental to long bearing life. Mobil Arapen RB 320 grease has exceptional ability to withstand shear, i.e. retain consistency after prolonged we as in the churning action of an anti-friction bearing. This grease has been shown to have little effect on seal materials. Largely because of its special calcium-lithium base, Mobil Arapen RB 320 grease has a high resistance to structural change in the presence of water. It is also inhibited to give protection against rusting.

Mobil Arapen RB 320 is fully approved against Specification M-942 of the Association of American Railroads for Journal Roller Bearings Grease for non-field lubr bearing applications. It is used by major manufacturers of railroad journal bearings as the factory-fill lubricant. Mobil Arapen RB 320 has an application temperature of -20°C to +120°C.

Features and Benefits

Mobil Arapen RB 320 railroad car journal bearing grease offers the following features and benefits:

- Approved against AAR specification AAR-942
- Formulated for long service life over a wide range of climatic conditions
- · Exhibits excellent oxidation stability, shear stability, seal compatibility, and water resistance for extended grease life and equipment integrity

Applications

- Roller bearings of railroad car journals where no provision is proided for in-service re-lubrication.
- Factory fill lubricant of major railroad journal bearing manufacturers

Specifications and Approvals

This product has the	e following approvals:
AAR-M942	

Properties and Specifications

Property	
Grade	NLGI 1.5
Thickener Type	Lithium Calcium
Color, Visual	Light Amber
Dropping Point, °C, ASTM D2265	180
Oxidation Stability, Pressure drop at 100hr, psi, ASTM D942	1
Oxidation Stability, Pressure drop at 500 hr, psi, ASTM D942	3

Mobil Arapen™ RB 320 Page 2 of 2

Property	
Penetration, 60X, 0.1 mm, ASTM D217	305
Penetration, Change from 60X to 100,000X, 0.1 mm, ASTM D217	+20
SKF Emcor Rust Test, Distilled Water, ASTM D6138	0,0
Viscosity @ 40 C, Base Oil, mm2/s, ASTM D445	152
Viscosity @ 100 C, Base Oil, mm2/s, ASTM D445	14.5
Viscosity Index, ASTM D2270	93

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

04-2024

Delta Panamá,

Cl. Miguel Brostella,

Edif. Camino de Cruces piso 7,

Panamá,

(+507) 279-3000

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All promany not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

