Mobil[®]

Mobilgrind Series

Mobil Industrial , Portugal

Neat honing and grinding fluids

Product Description

The Mobilgrind series of products are non-staining mineral oils intended for conventional and high speed grinding and honing applications across a wide ra materials and operations. The high quality base oils and select additive systems offer clear, low misting and low odor lubrication that help to improve the wor environment. Mobilgrind products are designed to prevent staining of non ferrous alloys and copper tubing that are often found in grinding oil circulation sy Mobilgrind oils separate readily from grinding swarf and components which helps to reduce drag off and waste generation. The products are readily filterable t increase surface finish accuracy. The Mobilgrind series is not formulated with any added zinc, chlorine or other materials that may require special disposal procedure

The Mobilgrind series can be used in centralized systems or in individual machine tools.

Mobilgrind 13 is intended for light duty honing and super finishing of a wide variety of steels and other alloys. It is clear, has neutral odour and low volatility proper help improve the working environment. Mobilgrind 13 can also be used as the dielectric fluid in Electro-Discharge Machining (EDM) applications.

Mobilgrind 14 is designed for light duty cylindrical and surface grinding of carbon and alloy steels. Formulated with high quality additives and base oils to help i misting and maintain viscosity at the point of application, Mobilgrind 14 helps retain accuracy in precision grinding applications. The low viscosity of the product fines to settle out quickly from the oil in sedimentation tanks and assists filtration of the oil for re-use in circulation systems

Mobilgrind 24 is medium duty product for honing and grinding applications on steels of a varying hardness. It is particularly well suited for rough and finish hor safety razor blades and for use in large volume circulation systems where continuous filtration is employed.

Mobilgrind 26 is a medium duty low viscosity fluid for finish grinding of hardened steels and other carbon alloys. Formulated with highly refined, high viscosity inde oils, Mobilgrind 26 helps ensure consistent viscosity at the point of application allowing good penetration and the efficient removal of fines from the cutting area . also be used for light duty machining operations where a low viscosity, low misting product is required.

Mobilgrind 36 is a medium/heavy duty product intended for finish grinding of hardened steels. It has excellent wettability to avoid burning and keep grinding v clean. Formulated with low viscosity, high quality base oils it is well suited for the finish grinding of precision gears, axles and other applications where a high dec precision is required.

Mobilgrind 37 is intended for medium/heavy duty form grinding applications such as mill and drill flute grinding. It helps to minimize staining of the flutes in thes speed operations. It may also be used as a hydraulic fluid in flute grinding applications where cross contamination of the hydraulic media could affect gr performance.

Features and Benefits

Features	Advantages and Potential Benefits
Low Misting and Neutral Odor	Enhances the workplace environment and reduces product usage
High Degree of Filterability	Reduced product usage and increased surface finish accuracy
Separates readily from swarf	Reduced product usage and ease of swarf disposal
Clear and chlorine free	Better work piece visibility and ease of disposal

Specifications and Approvals

This product has the following builder approvals:	13	14	24	26	36	37
KAPP GMBH	-	-	-	-	Х	-

Properties and Specifications

Property	13	14	24	26	36
ASTM Color, ASTM D1500	1.5	1		1	2
Copper Strip Corrosion, 3 h, 100 C, Rating, ASTM D130		1B	1B	1B	1B
Density @ 15 C, kg/l, ASTM D4052		0.78		0.79	
Density @ 15.6 C, kg/l, ASTM D4052	0.83				0.80
Flash Point, Cleveland Open Cup, °C, ASTM D92	120	150	130	170	180
Kinematic Viscosity @ 100 C, mm2/s, ASTM D445		2.0	2.5	3.0	2.5
Kinematic Viscosity @ 40 C, mm2/s, ASTM D445	4	6	7	12	15
Dielectric Strength, kv	28				

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

09-2021

ExxonMobil Lubricants and Specialties Europe division of ExxonMobil Petroleum & Chemical b.v.b.a. Polderdijkweg B-2030 Antwerpen, Belgium

http://www.exxonmobil.com

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All premay not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

