Mobil

MOBILCUT 100-NEW

Mobil Industrial , Turkey

Aqueous Metal Working Fluid

Product Description

Mobilcut is the trademark for Mobil Industrial lubricants line of high performance water miscible metal removal fluids. Formulated with leading edge base oils, addi and emulsifiers, the Mobilcut series of non-chlorinated products provides dependable performance in a wide array of metal removal processes. The product designed to work in a variety of hard and soft water qualities and offer low foam potential and long-term corrosion protection for machine and component: maintenance and inherently stable, Mobilcut products are designed for the modern machine shop where long service life, excellent machining performance, heal environmental concerns are important factors for increased productivity. These products are supplied in concentrated form and require mixing with water at the p use. All Mobilcut products are free of formaldehyde release agents (FAD).

Mobilcut 100-New is a conventional milky soluble oil that readily mixes with different waters to form stable emulsions. It shows good pH stability and especially si for harder water. Its versatile performance makes it suitable for a general machining of machine steels and copper alloys in light to moderate duty metalw operations such as milling, turning, sawing, boring, drilling and reaming.mixes with different waters to form stable emulsions. It shows good pH stability and esp suitable for harder water. Its versatile performance makes it suitable for a general machining of machine steels and copper alloys in light to moderate duty metalw operations such as milling, turning, sawing, boring, drilling and reaming.

Features and Benefits

The Mobilcut series are designed to help increase the productivity of modern machine shops by providing high performance features.

Features	Advantages and Potential Benefits
Form stable emulsions and solutions	Ease of use and maintenance
Long term inherent stability	Increases batch life and reduces unpleasant odors
Low foaming potential	Improved performance even in high pressure systems
Resists formation of sticky residues	Improves machine cleanliness
High degree of corrosion protection	Reduces machine maintenance and rework of materials
Good separability from fines	Improves filterability and surface finish
Wide Range of applicability	Potential to consolidate products and reduce inventories
Compatible with high performance Mobil Vactra Oil No slideway lubricants	Easy separation and removal of tramp oil
Neutral Odor	Enhances the workplace environment

Applications

Mobilcut 100-New: General machining of easy to machine steels and copper alloys in light to moderate duty machining operations such as milling, turning, s boring, drilling and reaming. Fluid type is milky emulsion. Mineral oil content is typically 70%. Optimal water hardness range is from 10 to 25 °dH and can go up to in use. Its refractometer factor is 1.0

Recommended concentrations for typical operations:

Low alloy steels - milling, turning: 7-12%

Carbon alloy steels, difficult machining: 7-12%

Aluminum machining: 7-12%

Properties and Specifications

Property	
Kinematic Viscosity 20 C, mm2/s, DIN EN ISO 3104	120
Density 15 C, kg/m3, DIN EN ISO12185	907
pH-Value 5.0% in 20 deg dH Water, DIN 51369	9
Appearance, AA.Lab.101	Liquid Brownish
Appearance, 5.0% in 20 deg dH Water, AA.Lab.101	Milky

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

06-2022 Mobil Oil Türk A.S. Pakpen Plaza Halk Sokak No: 40-44 34734 Kozyatagi Istanbul

You can always contact our Technical Help Desk engineers on Mobil lubricants and services related questions: https://www.mobiloil.com.tr/tr-tr/contact-us

Tel: +90 850 390 4939

http://www.mobiloil.com.tr

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product perform are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All premay not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

