



## Prowax™ 710

ExxonMobil Specialties , Australia

### Product Description

Prowax 710 is a low-range melting point product in the Prowax line of petroleum slack and scale waxes. It is a translucent crystalline material in the solid state and a straw yellow-to-amber, clear liquid when molten. It is derived from petroleum via a carefully controlled refining process. Prowax 710 is comprised of a mixture of straight chain normal paraffin and branched, iso-paraffin hydrocarbons.

ExxonMobil waxes are produced and controlled according to the ExxonMobil Product Quality Management System, EN ISO 9000 or equivalent standard.

### Applications

Prowax 710 can be used in the following applications subject to applicable laws and regulations in each jurisdiction\*:

- Wax emulsions
- Wax blends

\* User must check compliance with applicable regulations

### Properties and Specifications

| Property                                              | Standard Method(a) | Min         | Max         |
|-------------------------------------------------------|--------------------|-------------|-------------|
| Congealing Point, °C (°F)                             | ASTM D 938         | 46.0(114.8) | 56.0(132.8) |
| Oil Content, wt %                                     | ASTM D 3235        |             | 30.0        |
| Colour, ASTM                                          | ASTM D 6045        |             | 2.0         |
| Kinematic Viscosity @ 100°C, mm <sup>2</sup> /s (cSt) | ASTM D 445         | 3.5         | 4.5         |
| Flash Point COC, °C (°F)                              | ASTM D 92          | 204(400)    |             |

(a) In lieu of standard test method, alternate test methods may be used for the certification of a product property.

(b) Density at 15°C is based on measurement of the wax liquid density at a higher temperature corrected to 15°C using ASTM D1250 Table B.

Note 1: Products are certified on release to meet the values specified. Actual values may deviate within the established reproducibility of the test method specified.

Note 2: For purpose of determining conformance with specification, observed or calculated values shall be rounded off to the nearest unit in the last significant digit used in expressing the limiting value in accordance to the ASTM E 29 method

### Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

04-2024

Mobil Oil Australia Pty Ltd

A.B.N. 88 004 052 984

12 Riverside Quay

Southbank Vic 3006

+61 3 8633 8444

<http://www.exxonmobil.com>

Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly. This product data sheet is based on global product data sheets for use with products purchased in the U.S.

ExxonMobil

Exxon

Mobil

Esso

XTO  
ENERGY

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved