



Plastol™ 537

ExxonMobil Specialties , United Kingdom

Product Description

Plastol 537 is a paraffinic low-colour mineral oil, complying with the purity requirements defined by the United States Food and Drug Administration (FDA) in chapter 21 CFR 178.3620(c). Although less refined than other Plastol technical white oil grades, it has a markedly better colour and colour stability than conventional rubber process oils.

The quality of ExxonMobil White Oils is assured for every delivery. These products are produced and controlled according to the ExxonMobil Product Quality Management System, EN ISO 9000 or equivalent standard.

Applications

Elastomers

- Plastol 537 is recommended as an extender oil in EPDM or EPDM-based Thermoplastic Olefinics (TPO) and Thermoplastic Vulcanisates (TPV). It provides improved stability against colour and mechanical degradation of EPDM bales during storage, when compared to conventional extender oils. Due to a much higher degree of refining leading to very low sulphur content, Plastol 537 is also well adapted to peroxide curing of EPDM or Thermoplastic Vulcanisates (EPDM).

Regulations and Claims

This product meets

FDA 21 CFR 178.3620(c)

Properties and Specifications

| Property | Standard Method(a) | Typical | Min | Max |
|---|--------------------|---------|------------------|-------|
| Appearance | Visual | | Clear and Bright | |
| ASTM Color | ASTM D1500 | 0.5 | | 1.0 |
| Kinematic Viscosity @ 40 C, mm ² /s | ASTM D445 | | 90.0 | 116.0 |
| Kinematic Viscosity @ 100 C, mm ² /s | ASTM D445 | 11.4 | | |
| Density @ 15 C, kg/m ³ | ASTM D4052 | 880 | | |
| Pour Point, °C | ASTM D97 | | | -3 |
| Flash Point, Cleveland Open Cup, °C | ASTM D92 | | 240 | |
| Sulfur content, wt% | ASTM D4294 | | | 0.20 |

Note 1: Products are certified on release to meet the values specified. Actual values may deviate within the established reproducibility of the test method specified.

Note 2: For purpose of determining conformance with specification, observed or calculated values shall be rounded off to the nearest unit in the last significant digit used in expressing the limiting value in accordance to the ASTM E 29 method

(a) In lieu of standard test method, alternate test methods may be used for the certification of a product property.

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

02-2024

ExxonMobil Lubricants & Specialties Europe

Hermeslaan 2

1831 Machelen

BELGIUM

+32-2-722-2111

<http://www.exxonmobil.com>

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

ExxonMobil

Exxon Mobil  

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved