ExconMobil

Paving Bitumen 30/40 AF

ExxonMobil Asphalt , Senegal

PENETRATION GRADED BITUMEN PRODUCT

Product Description

Paving Bitumen 30/40 AF is a penetration graded bitumen product derived from specially selected crude oils via carefully controlled refining processes.

The quality of ExxonMobil products is assured for every delivery. They are produced and controlled according to the ExxonMobil Global Product Integrity Manag System, EN ISO 9000 or equivalent standard.

Applications

Paving Bitumen 30/40 AF grade is recommended for road construction. If other applications are considered, then users should conduct appropriate testing before users.

Properties & Specifications

Paving Bitumen 30/40 AF grade meets the following specification requirements:

Paving Bitumen grade			30/40 AF
Property	Unit	Test Method	
Penetration at 25°C	x 0.1 mm	EN 1426	30-40
Softening point	°С	EN 1427	52-60
Flash point (min)	°C	ISO 2592	240
Solubility in toluene (min)	% (m/m)	EN 12592	99.0

Resistance to hardening: Rolling Thin Film Oven Test at 163 °C (EN 12607-1)

- change of mass (max) +/-	%	EN 12607-1	0.5
- retained penetration (min)	%	EN 1426	53
- increase in softening point (max)	°C	EN 1427	8

Above specifications may be subject to change.

Health & Safety

Detailed health and safety information for this product is provided in the Material Safety Data Sheet (MSDS), available upon request through your loca representative or from www.ExxonMobil.com.

All trademarks used herein are trademarks of Exxon Mobil Corporation or one of its subsidiaries.

05-2020

Further Information

ExxonMobil supplies a full range of bitumen, waxes, white oils, process oils and a full range of other lubricants, fuels and chemical products worldwide. Please c your local ExxonMobil representative, or contact us at www.ExxonMobil.com, for more information on other products.

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

