E**∕xonMobi**l

Parvan™ 1451

ExxonMobil Specialties , Thailand

Product Description

Parvan 1451 is a high-range melting point product in the Parvan line of fully refined paraffin waxes. Parvan waxes meet the requirements for most industri applications and meet applicable Food and Drug Administration (FDA) requirements for food, health and cosmetic-related uses. Parvan 1451 is a translucent crys material in the solid state and a water white, low viscosity, clear liquid when molten. It is derived from petroleum via a carefully controlled refining process and is pr comprised of straight chain normal paraffin hydrocarbons, which impart excellent gloss and water repellent properties. Resistance to most acids and alkalis is goc low oil content ensures that Parvan 1451 does not stain coated materials.

Parvan 1451 contains an FDA approved oxidation inhibitor to enhance the natural resistance to oxidation.

Parvan waxes are biodegradable under composting conditions†

ExxonMobil waxes are produced and controlled according to the ExxonMobil Product Quality Management System, EN ISO 9000 or equivalent standard

†Parvan waxes are biodegradable according to ASTM D6400-12 using ASTM D5338-11

Applications

Parvan 1451 can be used in the following applications subject to applicable laws and regulations in each jurisdiction*:

- Candles
- Wax blends and emulsions
- Paper converting
- Paper cup and package coatings
- Cosmetic formulations
- Polishes and paste waxes
- PVC lubricants
- Adhesives
- Crayons
- Sun-checking waxes for rubber and tires

* User must check compliance with applicable regulations

Regulations and Claims

ASTM Biodegradable according to ASTM D6400-12 using ASTM D5338-11	This product meets or exceeds the require	ments of:
	ASTM Biodegradable according to ASTM	D6400-12 using ASTM D5338-11
FDA 21 CFR 178.3710	FDA 21 CFR 178.3710	

Properties and Specifications

Property	Standard Method(a)	Min	Max
ASTM Saybolt D156 Color (ASTM D6045 Acceptable)	ASTM D6045	28	

Parvan™ 1451

Property	Standard Method(a)	Min	Мах
Flash Point, Cleveland Open Cup, °C (F)	ASTM D92	210(410)	
Melting Point, °C (F)	ASTM D87	61.1(142)	63.9(147)
Odor, Wax	ASTM D1833		1
Oil Content, wt%	ASTM D721		0.75

Note 1: Products are certified on release to meet the values specified. Actual values may deviate within the established reproducibility of the test method specified.

Note 2: For purpose of determining conformance with specification, observed or calculated values shall be rounded off to the nearest unit in the last significant dig in expressing the limiting value in accordance to the ASTM E 29 method

(a) In lieu of standard test method, alternate test methods may be used for the certification of a product property.

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

02-2024 ExxonMobil Asia Pacific Ltd 1 HarbourFront Place #06-00 HarbourFront Tower One Singapore 098633

+65 6885 5000 http://www.exxonmobil.com

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

