



Prowaxx™1663 SW(プロワックス 1663 SW)

ExxonMobil Specialties, Japan

製品の概要

Prowaxx 1663 SWは、ExxonMobilワックスのプロワックスラインにおける、高品質の溶解性スラックワックス[SW]です。本製品は固体では半透明な結晶状ですが、溶解すると黄色の透明な液体となります。慎重に制御された精製プロセスを経て石油から生成され、主に直鎖標準パラフィンおよび分岐イソパラフィン炭化水素の混合物により構成されます。

ExxonMobilワックスは、ExxonMobil製品品質管理システム、EN ISO 9000あるいは同等の基準に従って生産、管理されています。

用途

PROWAXX 1663 SWは、以下の用途で使用可能であり、各管轄区の適用法規の対象となります*。

- ・ ファイヤーログ
- ・ ワックスエマルジョン
- ・ ワックスブレンド

* ユーザは適用法規の準拠を確認する必要があります。

代表性状

Prowaxx™1663 SW	標準メソッド(a)	最小	最大
自動三刺激値法によるASTMカラー	ASTM D6045		6.0
引火点、クリーブランド開放式試験、°C(F)	ASTM D92	232(450)	
動粘度@100°C、mm ² /s	ASTM D445	16.0	20.5
含油量、wt%	ASTM D721		5.0
凝固点、°C(F)	ASTM D938	68.0(154)	81.0(178)

注1: 本製品は、指定された値を満たしていることがリリース時に認定されています。実際の値は、指定された試験方法の確立された再現性の範囲内で逸脱する場合があります。

注2: 規格への適合性を判断するため、観測値または計算値は、ASTM E 29メソッドに従って制限値を表す際に使用される最後の有効数字に四捨五入するものとします。

(a) 標準試験方法の代わりに、代替試験方法を使用して製品特性を証明することができます。

健康と安全

本製品の健康と安全に関する情報については、<http://www.msds.exxonmobil.com/psims/psims.aspx>にある製品安全データシート(SDS)をご覧ください。

本書で使用されているすべての商標は、その他の記載がない限り、Exxon Mobil Corporationまたは同社の子会社の商標または登録商標です。

01-2024

ExxonMobil Asia Pacific Ltd

1 HarbourFront Place

#06-00 HarbourFront Tower One

Singapore 098633

+65 6885 5000

<http://www.exxonmobil.com>

Every care has been taken in the preparation of this information. To the extent permitted by applicable law, all warranties and/or representations, express or implied, as to the accuracy of the information are disclaimed, and no liability is accepted for the accuracy or completeness of the same.

ExxonMobil



© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved