



Prowax 610

ExxonMobil Specialties, Taiwan

石油疏松蜡

產品說明

Prowax 610 是 Prowax 石油疏松蜡和片状蜡系列中的低熔点产品。这是一种固态半透明晶体材料，熔融后为淡黄色到琥珀色的透明液体。它通过严格控制的提炼工艺从石油中提炼而来。Prowax 610 由直链正链烷烃和支链异链烷烃组成。

ExxonMobil 蜡产品的生产和控制遵循 ExxonMobil 产品质量管理体系、EN ISO 9000 或同等标准。

應用

根据各司法管辖区的适用法律和法规，Prowax 610 可用于以下应用*：

- 蜡乳液
- 混合蜡

* 用户必须检查是否符合适用法规

特性和規格

特性	标准方法(a)	典型值	最小值	最大值
100 C条件下的运动黏度, mm ² /s	ASTM D445		3.5	4.5
15 C条件下的密度, kg/m ³	ASTM D4052	833		
闪火点, Cleveland Open Cup, °C	ASTM D92		204	
凝结点, °C	ASTM D938		46.0	56.0
含油量, wt%	ASTM D721	20		25
针入度, 25 C, 0.1 mm	ASTM D1321	100		
ASTM颜色	ASTM D1500	L0.5		2.0

注释 1: 产品发布时经过认证，已达到指定值。实际值可能在指定测试方法确定的可重复性范围内偏移。

注释 2: 为了确定与规范的一致性，观测值或计算值应四舍五入到按照 ASTM E 29 方法表示极限值时使用的最后一个有效数位的最近单位

(a) 可以使用替代测试方法替代标准测试方法对产品属性进行认证。

健康與安全

如需有關此產品的健康與安全建議，請參閱物質安全資料表 (MSDS)，其網址為：<http://www.msds.exxonmobil.com/psims/psims.aspx>

除非另有提及，否則此處使用的所有商標皆為 Exxon Mobil Corporation 或其子公司的商標或註冊商標。

11-2019

ExxonMobil international Holding Inc. Taiwan Branch

6F, No 2, Section 1, Tun Hua South Road

Taipei Taiwan


+886 2 2734 6888

<http://www.exxonmobil.com>

Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly.

Energy lives here™

ExxonMobil



© Copyright 2003-2019 Exxon Mobil Corporation. All Rights Reserved