Mobilect™ 44 Page 1 of 2



#### Mobilect™ 44

Mobil Industrial, Bangladesh

Electrical insulating oils

### **Product Description**

Mobilect<sup>™</sup> 44 is a premium high grade inhibited naphthenic mineral insulating oil with high dielectric strength and reliable oxidation stability intended for transfo switchgears and other electrical equipment.

Mobilect 44 meets the IEC 60296 (04) specifications and ASTM D1275 / IEC 62535 / DIN 51353 corrosion tests requirements.

### Features and Benefits

- Mobilect 44 has reliable oxidation stability, low sludge and acid formation, in both ageing and oxidation test. It is high resistance to thermal and chemical degrada the presence of iron and copper. This reduces tendencies to produce sludges and oil-soluble oxidation products.
- The high dielectric strength of Mobilect 44 is a measure of the resistance of the oil to electric stress and is expressed in kV across a specified gap under test conc This is not a measure of the quality of the oil but of the absence of contaminants especially moisture, fibres and polar chemicals.
- Mobilect 44 excellent low temperature properties is free from wax even at low temperatures and thus circulates freely in outdoor applications. Its low visco excellent for heat transfer and also low evaporation loss.
- The low pour point of Mobilect 44 ensures a free flow in most conditions between the transformer and the conservator and maintains the reliability of tap change the lowest temperatures.
- Very low in suphur, Mobilect 44 is DBDS and PCB free.
- Mobilect 44 is metal passivator and deactivator free.

### **Applications**

- Mobilect 44 is recommended for use in power/distribution transformers, circuit breakers, rectifiers, switches and switchgears in which the oil is required as an insumedium or as a heat transfer medium.
- Mobilect 44 is to be used in applications requiring IEC 60296 (4) and ASTM D1275 specifications.

# Specifications and Approvals

# This product meets or exceeds the requirements of:

IEC 60296:2012 Special Applications

### **Properties and Specifications**

Property	
Interfacial Tension, mN/m, ISO 6295	47
Oxidation Stability, Total Acid Number, mgKOH/g, IEC 61125-METC	0.08
Dissipation Factor, after Oxidation, 90 C, IEC 60247	0.003
Oxidation Stability, Sludge, mass%, IEC 61125-METC	0.02
Breakdown Voltage, after Treatment, kV, IEC 60156	>70

Mobilect™ 44 Page 2 of 2

Property	
Corrosive Sulphur, DIN 51353	Non Corrosive
Acidity, mgKOH/g, IEC 62021	<0.01
Flash Point (PMCC), deg C, ISO 2719	144
Kinematic Viscosity @ 40C, cSt, ISO 3104	7.5 - 11
Breakdown Voltage, kV, IEC 60156	40-60
Pour Point, deg C, ISO 3016	<-45
Density @ 20C, kg/L, ISO 12185	>0.85

### Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

06-2023

MJL Bangladesh Limited

Mobil House, CWS (A) 13/A, Gulshan Avenue,

Bir Uttam Mir Shawkat Sarak, Dhaka-1212, Bangladesh.

Tel: +880258815895, Hot Line: 16669

http://www.exxonmobil.com

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All promay not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

