

**Mobilux™ EP 2 - WR**

Mobil Grease , 中国

Grease

**Product Description**

Mobilux™ EP 2 - WR is a lithium grease that is designed for the applications that demand the water resistance performance. It provides excellent protection against wash-out and water-spray off which makes it particularly suitable for equipment where moist or wet conditions are common. The recommended operating temperature range is from -20°C to 120°C. It is available in NLGI grade 2, with base oil viscosity ISO VG 220.

**Features and Benefits**

Mobilux EP 2 -WR can offer the following features and potential benefits:

Features	Advantages and Potential Benefits
Good resistance to water washout and spray-off	Helps assure proper lubrication and protection even in the most severe water exposure conditions
Highly adhesive and cohesive structure	Excellent grease tenacity, helps reduce leakage and extend re-lubrication intervals for reduced maintenance requirements

**Applications**

Mobilux EP 2 - WR is recommended to be used as the sealing and lubrication of machinery in a wide temperature range of -20 to 120°C, as well as the lubrication of rolling and sliding bearings and other friction parts of various mechanical equipment.

**Properties and Specifications**

Property	
Grade	NLGI 2
Thickener Type	Grease - Lithium
Penetration, Worked, 60X, 0.1mm, GB/T 269	280
Dropping Point, °C, GB/T 3498	190
Water Sprayoff, Loss, mass %, SH/T 0643	25
Appearance, Visual	Brown & smooth
Base Oil Viscosity, 40 C, mm <sup>2</sup> /s, GB/T 265	220
Water Washout, Loss @ 79 C, mass %, SH/T 0109	4

**Health and safety**

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>  
All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

05-2022

ExxonMobil (China) Investment Co. Ltd

17th Floor, Metro Tower

30 Tian Yao Qiao Road  
Shanghai 2000030  
China

+86 21 24076000

<http://www.exxonmobil.com>

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All properties may not be available locally. For more information, contact your local ExxonMobil contact or visit [www.exxonmobil.com](http://www.exxonmobil.com)

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entity.

**ExxonMobil**



© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved