Mobilgrease™ Special Page 1 of 2



# Mobilgrease<sup>™</sup> Special

Mobil Grease, Germany

Grease

### **Product Description**

Mobilgrease Special is a high performance extreme pressure lithium hydroxystearate grease. It is formulated to provide protection against wear, rust and corrosion, washout and high temperature oxidation. It also contains molybdenum disulphide (moly) for added wear protection.

Mobilgrease Special is a multi-purpose heavy duty automotive grease designed for use in passenger cars, trucks, farm tractors, contractor, construction, minir mobile equipment. The recommended operating temperature range is -20° to 130°C. Due to the extra antiwear protection provided by the addition of moly, Mobil Special is particularly suitable for heavily loaded bearings under fretting or oscillating or sliding motion.

#### Features and Benefits

Mobilgrease Special is a member of the Mobilgrease brand of products, which has gained a worldwide reputation for innovation and performance exce Mobilgrease Special grease products are designed by ExxonMobil formulation technologists and backed by our worldwide technical support staff.

Mobilgrease Special was designed as a multipurpose heavy-duty grease for wheel bearings and chassis components in a wide range of automotive and inc equipment. Mobilgrease Special offers the following features and potential benefits:

- · Reduced wear under heavy or shock loading and vibrations for equipment protection and extended life under severe operating conditions
- Extra protection against rust and corrosion for reduced maintenance and downtime
- · Good resistance to water washout ensures proper lubrication even in the presence of water contamination
- Good pumpability in centralised systems

### **Applications**

Mobilgrease Special is a multi-purpose heavy duty automotive grease designed for use in passenger cars, trucks, farm tractors, contractor, construction, minir mobile equipment. Specific applications include:

- Wheel bearings, especially under fretting, oscillating or sliding motion
- Chassis components operating under severe conditions

## Properties and Specifications

| Property   |            |
|--|------------|
| Grade  | NLGI 2     |
| Thickener Type   | Lithium    |
| Base Oil Viscosity of Greases @ 40 C, mm2/s, AMS 1697        | 160        |
| Color, Visual  | Gray-Black |
| Dropping Point, °C, ASTM D2265                               | 190        |
| Four-Ball Extreme Pressure Test, Weld Point, kgf, ASTM D2596 | 250        |
| Four-Ball Wear Test, Scar Diameter, mm, ASTM D2266           | 0.4        |
| Penetration, 60X, 0.1 mm, ASTM D217                          | 280        |
| Timken OK Load, kg, ASTM D2509                               | 40         |

Mobilgrease™ Special Page 2 of 2

| Property  |      |
|---|------|
| Corrosion Preventive Properties, Rating, ASTM D1743 | PASS |

#### Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

06-2022

EXXONMOBIL LUBRICANTS & SPECIALTIES EUROPE, A DIVISION OF EXXONMOBIL PETROLEUM & CHEMICAL, BVBA (EMPC)

**POLDERDIJKWEG** 

B-2030 Antwerpen

Belgium

You can always contact our Technical Help Desk engineers on Mobil lubricants and services related questions: https://www.mobil.com.de/de-de/kontakt

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All promay not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

