



Mobil Glygoyle™ 11, 22, and 30

Mobil Industrial , Spain

High Performance Lubricants

Product Description

Mobil Glygoyle™ 11, 22, and 30 oils are polyalkyleneglycol-based (PAG) high performance lubricants that provide outstanding lubrication in extreme-temperature bearing and circulation system applications in conditions well beyond the capabilities of mineral oils. They are shear-stable and have outstanding resistance to thermal degradation, oxidation and the formation of sludge and deposits. They incorporate a proprietary additive package designed to enhance EP/anti-wear protection, corrosion and rust protection and foam resistance without detracting from the intrinsic attributes of the PAG base oils.

Mobil Glygoyle 11,22, 30 have very high viscosity indices and, being wax-free, they have extremely low pour points. Their coefficients of friction and traction (for example, in non-conforming gear or bearing contacts) are lower than for mineral oils. These exceptional lubricity characteristics help deliver lower operating temperatures in many applications.

Mobil Glygoyle 11 ,22, and 30 have provided outstanding performance in the most severe industrial applications for more than 25 years. They are recommended by major plastic calendar, paper machine bearing, compressor and gear manufacturers, and are the products of choice for many severe service applications.

Features and Benefits

The Mobil Glygoyle brand of lubricants is recognised and appreciated around the world for its innovation and outstanding performance. The molecular design of polyalkyleneglycol synthetic products have been specially chosen for use in Mobil Glygoyle 11, 22, and 30 and demonstrate the continuing commitment to advanced technology to provide outstanding product performance. A key factor in the development of Mobil Glygoyle 11, 22, and 30 were the close contacts between our scientists and application specialists with key OEMs to ensure that our product offerings will provide exceptional performance in the continually evolving industrial equipment designs.

Mobil Glygoyle products were primarily designed to meet the critical high temperature needs of a variety of industrial equipment where mineral-based and synthetic products were not able to perform satisfactorily. Additional features such as low friction and traction, gas absorption properties resulted in even broader industrial application opportunities. Mobil Glygoyle 11, 22, and 30 lubricants offer the following features and potential benefits:

| Features | Advantages and Potential Benefits |
|---|--|
| Superb thermal and oxidative stability, and resistance to sludge and deposit formation | Extended lubricant life, increased production, less scheduled and unscheduled downtime Lower maintenance costs and replacement expenditures |
| Low coefficients of traction and friction | Reduced operating temperatures, greater equipment efficiency, and potential for reduced power consumption and long seal life. Minimizes effects of micro slip in rolling contact bearings for longer element life potential |
| Very high thermal conductivity | Helps to lower operating temperature, increasing charge life. |
| Excellent low-temperature fluidity | Enables quicker warm-up at low ambient temperature resulting in reduced power consumption and smoother running. |
| Reduced gear tooth wear at high temperatures for both steel-on-steel and steel-on-bronze metallurgies | Reduced operating costs due to less wear, reduced operating temperature and smoother running |
| Reduced absorption and viscosity reduction with pressurised hydrocarbon gases | Improved film protection and long life for natural gas compressors |
| Multipurpose industrial equipment capability | Potential to use fewer products with reduced inventory costs and less chance of mis-lubrication |

Applications

Mobil Glygoyle lubricants are recommended for the most severe conditions in all types of plain and anti-friction bearings and industrial enclosed gears up to a maximum temperature of 200° C. Specific applications include:

- Severe plastic calendar operations
- High temperature paper machine bearings
- Industrial enclosed gears – spur, bevel and worm gearing
- Reciprocating and rotary air, natural gas, CO₂ and other process gasses

Application notes

Polyalkyleneglycol (PAG) based lubricants have some inherent excellent lubrication properties imparted by the PAG base oil. However, PAG based lubricants do have limitations with respect to compatibility with seal and coating materials, some varieties of light metal alloys and other lubricants. Before applying any PAG lubricant, contact the original equipment manufacturer for specific advice on the application.

Compatibility with other lubricants

Mobil Glygoyle 11, 22, and 30 are not compatible with mineral oils and most other synthetic lubricants. Additionally, depending on the specific type of PAG base oil, they may not be compatible with other PAG type lubricants. (e. g. Mobil Glygoyle 11, 22, 30 and Mobil Glygoyle ISO VG Series are not miscible) Mobil Glygoyle 11, 22, and 30 are not generally recommended for use in systems previously filled with mineral oils or PAO based synthetic lubricants. It is further recommended to avoid compatibility when topping up or replacing existing PAG fillings with Mobil Glygoyle products, generally the preference is to avoid mixtures by draining, flushing and refilling. When changing from mineral oil or other synthetic products to Mobil Glygoyle products, it is critical to clean the system thoroughly and flush with suitable oil prior to conversion. For further details please contact your ExxonMobil representative.

Water

Mobil Glygoyle 11, 22, and 30, along with all PAG based lubricants, are hygroscopic and absorb more water than mineral oils or synthetic hydrocarbons before. The extra care should be taken not to expose PAG oils to excessive moisture. Due to their inherent high specific gravity, water does not drop to the bottom of reservoirs but stays on top of the lubricant.

Seal compatibility

PAG based lubricants are not compatible with most standard seal materials used for mineral oils or synthetic hydrocarbons. Incompatible materials are likely to swell, thus causing severe leakage or seizure of the seal. When converting from mineral oil or synthetic hydrocarbons to Mobil Glygoyle 11, 22, or 30, seal compatibility must be considered. FKM and VMQ are normally suitable for use with PAG. NBR materials may be used but have restricted temperature range. In all cases, operating conditions and the variability of elastomer properties from different manufacturers should be considered. For best results, consult the equipment supplier or seal manufacturer for specific recommendations.

Light Metal Alloys

Mobil Glygoyle 11, 22, and 30 and PAG lubricants are well suited for gear applications with ferrous and most non ferrous materials. However, Mobil Glygoyle products and PAG lubricants are not recommended for use with light metal alloys containing Aluminum or Magnesium. PAG lubricants can lead to increased wear when used with light metal alloys of this nature. Please consult the original equipment manufacturer for additional information.

Other Materials

Paints, coatings, and some plastics are not suitable for use with PAG lubricants. In general two component paints (reactive paints, epoxy resins) are suitable for use as interior coatings in contact with the lubricant. Otherwise, interiors in contact with the lubricant should be left uncoated. Materials used for oil level gauges, inspection doors etc., should preferably be made of natural glass or polyamide materials. Other transparent plastics, e.g. Plexiglas, may deteriorate and crack under stress.

Properties and Specifications

| Property | MOBIL GLYGOYLE 11 | MOBIL GLYGOYLE 22 | MOBIL GLYGOYLE 30 |
|--|-------------------|-------------------|-------------------|
| Copper Strip Corrosion, 24 h, 100 C, Rating, ASTM D130 | 1B | 1B | 1B |
| FZG Scuffing, Fail Load Stage, A/8.3/90, ISO 14635-1 | 12+ | 12+ | 12+ |
| Flash Point, Cleveland Open Cup, °C, ASTM D92 | 226 | 229 | 221 |
| Foam, Sequence I, Stability, ml, ASTM D892 | 0 | 0 | 0 |
| Foam, Sequence I, Tendency, ml, ASTM D892 | 5 | 5 | 5 |

| Property | MOBIL GLYGOYLE 11 | MOBIL GLYGOYLE 22 | MOBIL GLYGOYLE 30 |
|--|-------------------|-------------------|-------------------|
| Four-Ball Wear Test, Scar Diameter, mm, ASTM D4172 | 0.4 | 0.4 | 0.4 |
| Kinematic Viscosity @ 100 C, mm2/s, ASTM D445 | 11.5 | 25.1 | 30.9 |
| Kinematic Viscosity @ 40 C, mm2/s, ASTM D445 | 85 | 177 | 224 |
| Pour Point, °C, ASTM D97 | -45 | -41 | -41 |
| Rust Characteristics, Procedure A, ASTM D665 | PASS | PASS | PASS |
| Specific Gravity, 20 C/20 C, ASTM D1298 | 1.009 | 1.007 | 1.006 |

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.as>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

02-2024

ExxonMobil Lubricants and Specialties Europe division of ExxonMobil Petroleum & Chemical b.v.b.a.

Polderdijkweg

B-2030 Antwerpen, Belgium

<http://www.exxonmobil.com>

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect pro performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without nc All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intende override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

ExxonMobil

Exxon

Mobil

Esso

XTOMobil

© Copyright 2003-2024 Exxon Mobil Corporation. All Rights Reserved