Mobilect™ 39 Page 1 of 2



Mobilect™ 39

Mobil Industrial , Italy

Electrical insulating oils

Product Description

Mobilect™ 39 is a high quality mineral uninhibited insulating oil with very good dielectric properties and oxidation stability intended for transformers, switchgea other electrical equipment.

Mobilect 39 is uninhibited and meets the specifications IEC 60296 (04) and ASTM D1275B / CIGRE corrosion tests requirements.

Features and Benefits

- Mobilect 39 has a high resistance to thermal and chemical degradation in the presence of iron and copper, which reduces tendencies to produce sludge and oil-s oxidation products. When lower quality oils are used these may form deposits in the transformer and impede heat transfer by interfering with convection curre addition deposits may accelerate insulation defects and are often very difficult to remove without complete dismantling.
- Mobilect 39 is specifically treated during manufacture to remove moisture. Water will reduce the electrical insulating properties of the oil and promote oxidatic important to remember that a dry oil is hygroscopic and absorbs moisture from the air. It must therefore always be stored in dry conditions and well-closed contains strongly recommended to dry the product before use or use it within short notice after purchasing to avoid long term storage.
- The dielectric strength of Mobilect 39 is a measure of the resistance of the oil to electric stress and is expressed in kV across a specified gap under test conditions. not a measure of the quality of the oil but of the absence of contaminants especially moisture, fibres and polar chemicals.
- Mobilect 39 is free from wax even at low temperatures and thus circulates freely in outdoor applications. Its viscosity ensures readily heat transfer by mobile convcurrents. Mobility is also essential to quick quenching of arcs in switchgear units.
- The low pour point of Mobilect 39 ensures a free flow in most conditions between the transformer and the conservator and maintains the reliability of tap change the lowest temperatures.

Applications

- Mobilect 39 is recommended for use in oil filled transformers andwitchgears in which the oil is required as an insulation medium or as a heat transfer medium.
- Mobilect 39 is to be used in applications specifying IEC 60296 (04) General Specifications and reinforced copper corrosion protection (pass ASTM D1275B cortest).
 - Mobilect 39 is not suitable for use in oil filled cables, for special impregnation processes or for use in capacitors.

Specifications and Approvals

This product meets or exceeds the requirements of:

IEC 60296 (04) General Specifications

Properties and Specifications

Property	
Breakdown Voltage, kV, IEC 60156	> 30
Breakdown Voltage, after Treatment, kV, IEC 60156	>70
Corrosive Sulfur, Procedure B, ASTM D1275	Non Corrosive
Density @ 20C, kg/L, ISO 12185	0.883

Mobilect™ 39 Page 2 of 2

Property	
Dielectric Dissipation Factor @ 90 C, IEC 60247	<0.001
Flash Point, Pensky-Martens Closed Cup, °C, ISO 2719	148
Interfacial Tension, mN/m, ISO 6295	> 40
Kinematic Viscosity @ 40 C, mm2/s, ISO 3104	9.5
Oxidation Stability, Sludge, 164 h, 120 C, mass%, IEC 61125-METC	0.11
Oxidation Stability, Total Acidity, 164 h, 120 C, mgKOH/g, IEC 61125-METC	0.31
Pour Point, °C, ISO 3016	-54

Health and safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ http://www.msds.exxonmobil.com/psims/psims.as All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

Esso Italiana s.r.l.

11-2022

Via Castello della Magliana 25 00148, Roma, Italia

You can always contact our Technical Help Desk engineers on Mobil lubricants and services related questions: https://www.mobil.it/it-it/contact-us

800.011723

http://www.exxonmobil.com

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All promay not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

