Mobilux™ EP 111 Page 1 of 2



Mobilux™ EP 111

Mobil Grease, Pakistan

Grease

Product Description

Mobilux EP 111 is an extra high performance grease primarily designed for lubrication of all AGMA CG-3 couplings. It is specifically formulated to help protect ϵ wear even in heavily loaded misaligned low speed gear couplings. Mobilux EP 111 is a lithium hydroxystearate grease formulated with an extremely heavy, ν mineral base oil. Mobilux EP 111 also contains an oil soluble molybdenum additive, as well as a very effective corrosion inhibitor. It is an NLGI 1 Grade grease.

Mobilux EP 111 has shown excellent performance and protection in a broad range of industries. Based on its longstanding performance capabilities, this grea become the product of choice for many users.

Features and Benefits

The Mobilux brand of products is well known and highly regarded world-wide based on their very good performance over an extended period. The excellent qual one of these lubricants in this family, Mobilux EP 111, have made it the choice of many users.

Mobilux EP 111 enjoys an excellent reputation in the lubrication of all types of heavily loaded couplings in a wide variety of applications, and offers the foll advantages and potential benefits:

Features	Advantages and Potential Benefits		
Very good viscometrics and wear protection	Extended coupling protection and coupling life: helping to reduce maintenance replacement costs		
Resists oil separation	Less oil leakage helping to reduce lubricant consumption		
Good high temperature stability	Long grease life helping extend relubrication intervals		
Good resistance to rust and corrosion	Maintains grease performance even in presence of water		

Applications

Mobilux EP 111 is recommended for all types of heavily loaded lubricated couplings. Mobilux EP 111 has a recommended operating temperature range of -10 to 1 Mobilux EP 111 has performed very well in the following applications:

- Gear and grid couplings
- Spring and slipper joint couplings
- Spindle (gear) and chain couplings
- Low speed open gears and plain bearings

Specifications and Approvals

This product meets or exceeds the requirements of:	
AGMA CG-3	

Properties and Specifications

Prope	erty					
-------	------	--	--	--	--	--

Mobilux™ EP 111 Page 2 of 2

Property	
Grade	NLGI 1
Thickener Type	Lithium
Base Oil Viscosity of Greases @ 100 C, mm2/s, AMS 1700	45
Color, Visual	Black
Corrosion Preventive Properties, Rating, ASTM D1743	PASS
Dropping Point, °C, ASTM D2265	180
Four-Ball Extreme Pressure Test, Weld Load, kgf, ASTM D2596	315
Four-Ball Wear Test, Scar Diameter, 40 kg, 1200 rpm, 1 h, 75 C, mm, ASTM D2266	0.4
Penetration, 60X, 0.1 mm, ASTM D217	325
Timken OK Load, lb, ASTM D2509	50

Health and safety

 $Health \ and \ Safety \ recommendations \ for \ this \ product \ can \ be \ found \ on \ the \ Material \ Safety \ Data \ Sheet \ (MSDS) \ @ \ http://www.msds.exxonmobil.com/psims/psims.as$

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

02-2023 Mobil Askari Lubricants Limited D-46, Block-5 KDA Scheme-5, Clifton Karachi, Pakistan

Phone: (92-21) 111-840-840 Fax: (92-21) 583-1013 and 583-0082

http://www.exxonmobil.com

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All promay not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intenoverride or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entit

